



SOLUTIONS

ENVIRONMENTAL PROTECTION, INC.

1567 W. South Airport Rd.
Traverse City, Michigan
49686

Phone | 800-OK-LINER
Fax | 231-943-2270

www.geomembrane.com

10 mil PVC Geomembrane Specifications

TYPICAL APPLICATIONS:

Reservoirs

Canals

Farm Ponds

Water Features

Irrigation Ponds

Golf Course Ponds

Decorative Ponds

Oil Well Drilling Pits

Oil Reserve Pit

Closures

PVC liners fabricated by EPI are a single-ply construction with Polyvinyl Chloride as the principle polymer. Only first quality virgin resins are used and all materials meet or exceed the requirements of ASTM D7176 Standard Specification for PVC geomembranes used in buried applications.

EPI utilizes statistical process control (SPC) to ensure the integrity of each panel produced. Samples from actual factory seams are removed during the welding process for a rigorous, proven testing procedure that assures you of the highest quality factory-fabricated PVC geomembranes available.

PVC Liners are fabricated by EPI in panels, accordion-folded in both directions, and packaged for shipment to your site for quick, easy installation to save you time and money.

Thickness ± 5%	ASTM D-5199	.010"
Specific Gravity (min)	ASTM D-792	1.20

Tensile (lb/in-width, min)	ASTM D-882	24
----------------------------	------------	----

Elongation at Break (% min)	ASTM D-882	250
-----------------------------	------------	-----

Modulus (lb/in-width, min)	ASTM D-882	10
----------------------------	------------	----

Tear Resistance (lb/in, min)	ASTM D-1004	2.5
Resistance to Soil Burial (% change, max)	ASTM G-160	

1. Breaking Factor		5
2. Elongation At Break		20
3. Modulus at 100% Elongation		20

Impact Cold Crack (°C)	ASTM D-1790	-23
Dimensional Stability (% change, max)	ASTM D-1204 (212°F/15 min.)	4

Water Extraction (% max)	ASTM D-1239	0.15
Volatile Loss (% max)	ASTM D-1203(A)	1.5
Hydrostatic Resistance (psi, min)	ASTM D-751(A)	42
Plasticizer Min Ave Molec Wt	ASTM 2124	400

Factory Fabricated Seams:

Peel Strength (lbs/in, min)	ASTM D-7408	10/FTB
Shear Strength (lbs/in, min)	ASTM D-7408	20

These data are based on tests believed to be reliable. However, these are laboratory tests that may not simulate actual use conditions. They are provided for your informational purposes only. No warranty, express or implied, including any other further warranty of fitness for a particular purpose or merchantability, is made by this promotional literature

Preserving water resources for future generations

DISTRIBUTOR

ASP Enterprises-STL
1099 Cassens Ind. Ct.
Fenton, MO 63026
TF: 800-869-9600
www.aspent.com

ASP Enterprises-KC
5301 E. 59th St.
Kansas City, MO 64130
TF: 800-519-2304
www.aspent.com

ASP Enterprises-Omaha
15263 Cooper St.
Omaha, NE 68138
TF: 877-678-8027
www.aspent.com