



## Specification Sheet – VMax® W3000™ High-Performance Turf Reinforcement Mat

### DESCRIPTION

The VMax® W3000™ high performance turf reinforcement mat (HPTRM) is a machine-produced mat of 100% UV-stabilized high denier poly yarns woven into permanent, high strength three-dimensional turf reinforcement matting. The mat consists of a woven bottom layer integrally interlaced into a woven corrugated middle layer, with poly tendons on the top side spanning the entire machine direction. The mat is designed to provide sufficient thickness, optimum open area and three-dimensionality for effective erosion control and vegetation reinforcement against high flow induced shear forces. The mat has high tensile strength providing excellent damage resistance and increased bearing capacity of vegetated soils subject to heavy loads from maintenance equipment and other vehicular traffic. The corrugated structure provides a highly frictional surface to prevent sod slippage when sod is installed over the mat. When used as surface protection without sod overlay, the corrugated structure encapsulates the seed and soil in place while promoting self-soil infilling of the system.

#### Material Content

	Material Content	
<b>Bottom</b>	100% UV stable poly fiber weave	Black/Green
<b>Corrugated Middle</b>	100% UV stable poly fiber weave	Black/Green
<b>Top</b>	100% UV stable Poly Tendons	Green

#### Standard Roll Sizes

	10 ft (3.05 m)	10 ft (3.05 m)	10 ft (3.05 m)
<b>Width</b>	10 ft (3.05 m)	10 ft (3.05 m)	10 ft (3.05 m)
<b>Length</b>	45 ft (13.7 m)	72 ft (21.9 m)	90 ft (27.4 m)
<b>Weight ± 10%</b>	45 lbs (20.4 kg)	72 lbs (32.7 kg)	90 lbs (41.0 kg)
<b>Area</b>	50 sy (41.8 sm)	80 sy (66.89 sm)	100 sy (83.6 sm)

Index Property	Test Method	Typical
<b>Thickness</b>	ASTM D6525	0.40 in. (10.2 mm)
<b>Resiliency</b>	ASTM D6524	98%
<b>Mass/Unit Area</b>	ASTM 6566	14.7oz/sy (495 g/m <sup>2</sup> )
<b>Tensile Strength - MD</b>	ASTM D6818	3600 lbs/ft (52.6 kN/m)
<b>Elongation - MD</b>	ASTM D6818	35%*
<b>Tensile Strength - TD</b>	ASTM D6818	3800 lbs/ft (55.5 kN/m)
<b>Elongation - TD</b>	ASTM D6818	20%*
<b>Light Penetration</b>	ASTM D6567	12%
<b>UV Stability</b>	ASTM D4355	>80% @3000 hrs

\* Measured on fabric prior to corrugation for true measurement of base fabric elongation

#### Design Permissible Shear Stress\*

<b>Vegetated Shear Stress</b>	16 psf (766 Pa)
<b>Vegetated Velocity</b>	25 fps (7.6 m/s)

\*Values extrapolated through ASTM D6460 testing

#### ASTM D6460 Large Scale Channel

<b>Vegetated Shear Stress</b>	>13.2 psf (632 Pa)
<b>Vegetated Velocity</b>	>24.5 fps (7.47 m/s)

Distributed by:



www.aspent.com (800) 869-9600



North American Green  
5401 St. Wendel-Cynthiana Road  
Poseyville, Indiana 47633

nagreen.com  
800-772-2040

©2017, North American Green is a registered trademark. Certain products and/or applications described or illustrated herein are protected under one or more U.S. patents. Other U.S. patents are pending, and certain foreign patents and patent applications may also exist. Trademark rights also apply as indicated herein. Final determination of the suitability of any information or material for the use contemplated, and its manner of use, is the sole responsibility of the user. Printed in the U.S.A.